

DIALOG(R)File 347:JAPIO

(c) 1999 JPO & JAPIO. All rts. reserv.

05375102 **Image available**

MANUFACTURE OF SEMICONDUCTOR DEVICE

PUB. NO.: 08-330602 [JP 8330602 A]

PUBLISHED: December 13, 1996 (19961213)

INVENTOR(s): TANAKA KOICHIRO
 ONUMA HIDETO

APPLICANT(s): SEMICONDUCTOR ENERGY LAB CO LTD [470730] (A Japanese Company
 or Corporation), JP (Japan)

APPL. NO.: 08-097478 [JP 9697478]

FILED: March 27, 1996 (19960327)

INTL CLASS: [6] H01L-029/786; H01L-021/336; H01L-021/20; H01L-021/268;
 H01L-021/322; H01L-021/324

JAPIO CLASS: 42.2 (ELECTRONICS -- Solid State Components)


JAPIO KEYWORD: R002 (LASERS); R004 (PLASMA); R096 (ELECTRONIC MATERIALS --
 Glass Conductors); R097 (ELECTRONIC MATERIALS -- Metal Oxide
 Semiconductors, MOS); R100 (ELECTRONIC MATERIALS -- Ion
 Implantation)

ABSTRACT


PURPOSE: To enhance the characteristics of a semiconductor device,
utilizing a metal element which accelerates crystallization of Si.

CONSTITUTION: A thin film transistor is constituted, using a crystalline Si
film obtained by utilizing a metal element, Ni, which accelerates the
crystallization of Si. A source region 108 and drain region 109 are
produced with Ni by implanting ions of an element, P, for gettering Ni and
annealing to getter Ni. For forming a P-channel type thin film transistor,
for example, both phosphorus and boron are used; phosphorus determining the
conductivity and boron being used for gettering.


【図1】




【図2】



【図3】



【図4】



フロントページの続き

(51) Int. Cl. 6
H01L 21/324

識別記号 庁内整理番号

FI
H01L 29/78

技術表示箇所

616A
627G